

Product

PRIMER 0230

code 6360 M040

**PRIMER FOR CONCRETE. MOISTURE CURING POLYURETHANE RESIN BASED.
SPECIAL PRIMER FOR POLYURETHANE SEALER AND MOISTURE-CURING POLYURETHANE MEMBRANE.**

Technical data

Colour	Amber
Specific weight at 20°C	1±0.01 kg/l
Viscosity at 20°C	30±10 mPa.s (speed 100 – Gr.1)
Solids	46% by weight 40% by volume
Theoretical consumption	150 g/m ²
ASTM D 4541 adhesion to concrete	>3 MPa
Overapplication time at 22°C, 50% RH	20 minutes minimum 60 minutes maximum
Storage	12 months from date of production if stored properly in original, unopened sealed packaging, in a dry place at temperatures between +5°C and +35°C.

The data and prescriptions contained in this schedule, based on the best practical and laboratory experiences, are to be considered in any case indicative. Given the different conditions of use, and the intervention of factors independent of MPM (support, environmental conditions, technical direction of application, etc.) those intending to use the product are held to establish whether it is suitable or not for the intended use. Our guarantee extends only to the quality and consistency of the finished product with the data given above, and only for technical schedules bearing the stamp and countersignature of the personnel delegated by our offices. The customer is further held to verify that these values are valid for the product batch concerning him and have not be updated and/or substituted by subsequent issues and/or new formulations. The data contained may vary at any moment without any obligation on the part of MPM to give prior notice.