

**Product**

# STARFLEX MONO TOP

**ONE COMPONENT ELASTIC ALIPHATIC POLYUREA BASED TOP COAT**

**Features**

- Easy to apply by means of brush, roller or airless spray.
- Anti-slip achievable.
- High elasticity.
- Resistant to abrasion, atmospheric agents and UV rays (not yellowing).
- Substrate application temperature range: from + 5 ° C to + 35 ° C (R.H. < 85%).
- Operating temperature -40°C - +120°C in air.

**Application fields**

Protective UV ray resistant top coat for STARFLEX range of products.  
 High resistance top coat for pedestrian or car traffic passage.

**Application**

Neutral converter product to be coloured with pigment pastes at the time of use.  
 STARFLEX MONO TOP can be applied at a rate of 0.150-0.600 kg/m<sup>2</sup> per each single coat  
 The use of STARFLEX MONO TOP with a broadcast of quartz with a suitable grain size makes the product highly anti slip.  
 When 2 coats must be applied do not leave more than 48 hours between coats.

Clean the tools thoroughly with DILUENTE 6 after use.

**Technical Data**

<b>Colour</b>	White, light and dark grey, oxide red and green. Organic dyes.
<b>Specific weight</b>	1,31±0,07 kg/l
<b>Viscosity at 20°C UNI EN ISO 2555</b>	2500 ± 500 mPa.s
<b>Solid content EN ISO 3251</b>	65% in volume 75 ± 1 in weight
<b>Theoretical consumption</b>	150-400 g/m <sup>2</sup> per coat It depends on the colour
<b>Theoretical thickness</b>	67÷180 µm per coat
<b>Storage</b>	When kept in the original sealed packs in a dry protected place at temperatures from + 5°C to + 35°C, the product will keep for 12 months.

The data and prescriptions contained in this schedule, based on the best practical and laboratory experiences, are to be considered in any case indicative. Given the different conditions of use, and the intervention of factors independent of MPM (support, environmental conditions, technical direction of application, etc.) those intending to use the product are held to establish whether it is suitable or not for the intended use. Our guarantee extends only to the quality and consistency of the finished product with the data given above, and only for technical schedules bearing the stamp and countersignature of the personnel delegated by our offices. The customer is further held to verify that these values are valid for the product batch concerning him and have not be updated and/or substituted by subsequent issues and/or new formulations. The data contained may vary at any moment without any obligation on the part of MPM to give prior notice.

